










Nexus, Glazed Porcelain.

Technical information

Tile collection performance based on industry standards.

Technical Information

| | | | |
|---|---------------------|------------------------------------|----------------------------|
|  | WATER ABSORPTION | ANSI / ISO - (%) | < 0.5% |
|  | ABRASION RESISTANCE | ANSI / ISO | CLASS 4 |
|  | SCRATCH HARDNESS | ANSI / ISO - (Mohs) | 7 |
|  | BREAKING STRENGTH | ANSI - (lbf) ISO - (N) | ≥450 ≥2000 |
|  | SHADE VARIATION | | V3 |
|  | SLIP RESISTANCE | ANSI - DCOF (WET) ISO - R VALUE | MATTE ≥0.50 MATTE R (-) |
|  | CHEMICAL RESISTANCE | ANSI / ISO | CLASS A |
|  | STAIN RESISTANCE | ANSI ISO | CLASS A CLASS 5 |
|  | FROST RESISTANCE | ANSI / ISO | PASS |

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

Usage recommendations

Anatolia's recommendations for suitable applications.

| Usage Recommendations* | | MATTE GLAZED PORCELAIN | |
|------------------------|--------------------------|------------------------|-------|
| APPLICATION | | WALL | FLOOR |
| INTERIOR | RESIDENTIAL | • | • |
| | COMMERCIAL | • | • |
| | HEAVY COMMERCIAL | • | |
| EXTERIOR | RESIDENTIAL / COMMERCIAL | • | |

* These recommendations are not defined by ANSI/ISO standards.